

TIKKURILA

SUPI ARCTIC

SAUNA FINISH FOR PANELS / PEARLESCENT



DESCRIPTION Pearl shining, tintable acrylate protective agent.

RECOMMENDED USES Especially for walls and ceilings in steam, washing and dressing rooms.

PRODUCT FEATURES A finish for humid interior spaces that forms a dirt- and water-repellent surface. Contains an antimold agent that protects the treated surface. Suitable for treatment of wood surfaces according

to instructions. Not suitable for treatment of sauna benches.







SUPI ARCTIC

TECHNICAL DATA

Base paints EP BASE

Colour Shades Color cards:

Arctic.

Can be tinted in Tikkurila translucent Arctic colors.

Gloss Semi-matt.

Coverage 8-12 m²/l

Can sizes 0.9 l, 2.7 l

Application method Brush.

Drying time (23°C and

50% relative air humidity)

Dust dry after 30 min. Next coat can be applied after 2-3 hours. Dry to use after

about 2 days.

Density (kg/l) 1.0 kg/l, ISO 2811

Volume solids (%) 17

VOC (cat A/f) 130g/l(2010)

Supi Arctic contains VOC max. 130 g/l.

Storage Protect from frost.



SUPI ARCTIC

APPLICATION INSTRUCTIONS

Application conditions

The surface to be treated must be dry, the ambient temperature at least +5 °C and the relative humidity of air below 80%.

Surface preparation

New clean wood surfaces:

Clean the wood surface of any dirt and dust. Wet the surface lightly with water spray, let dry and sand off the loose wood fibers. Remove the sanding dust.

Old and dirty surfaces or surfaces previously treated with, e.g. Supi Saunasuoja:

Wash with Supi Saunapesu cleaning agent according to instructions, rinse thoroughly and let dry. If needed, sand and dust off.

Application

Stir Supi Arctic thoroughly, also from time to time during usage.

Treat steam room walls once with tinted Supi Arctic. Thin with water if necessary.

You can also treat the steam room walls twice with Supi Arctic thinned with water up to 50 %. This way the brush marks will be less noticeable.

First treat washing and dressing room surfaces with Supi Arctic thinned with 20 % of water, then with unthinned Supi Arctic.

Make a trial application in a inconspicuous spot to ensure that the color is correct. When the product is thinned the color becomes a little lighter and more transparent than in the color card. The properties of the wood and previous treatments influence the final color. Treat small surfaces in one go without interruptions and large panel surfaces 1-2 panels at a time in order to achieve a uniform color. You can achieve a matching color on sauna benches – without the pearl effect – by tinting Supi Saunavaha wax according to the Valtti Arctic color card.

Pre-heat and ventilate the sauna thoroughly before use.

Cleaning of tools

Clean the tools with water and soap Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint. Clean the tools with water and soap Tikkurila Pensselipesu Tool Cleaner is recommended to remove slightly hardened paint.

Maintenance instructions

Cleaning about 1 month after application at the earliest:

Clean the surface with Supi Saunapesu cleaning agent (1-2 dl of cleaning agent into 5 liters of water).

Environmental protection and waste disposal

Destroy liquid waste according to the local regulations for hazardous waste. Recycle empty, dry cans or dispose them of in accordance with local regulations.



SUPI ARCTIC

Health and Safety

Harmful to aquatic life with long lasting effects. Contains 1,2-benzisothiazol-3(2H)-one (BIT), reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)) and 2-octyl-2H-isothiazol-3-one (OIT). May produce an allergic reaction. Avoid release to the environment. Wear protective gloves. This product contains a biocidal product for the preservation of the product during storage. Contains C(M)IT/MIT.

This paint contains a biocidal product for the preservation of the dry film. Contains OIT, 3-iodo-2-propynyl butylcarbamate. Risk of skin sensitisation.