



JO-XXM750

Extreme Resistance Acrylic Top Coat

Main properties:

<ul style="list-style-type: none"> Extremely resistant to "nail polishing", even in low-gloss versions Excellent hardness, far higher than traditional products Extreme film elasticity 	<ul style="list-style-type: none"> It can be used as basecoat Non yellowing Excellent protection of the substrate against yellowing
--	--

Versions:

- JO-02M750:** 2÷3 Gloss
- JO-05M750:** 4÷7 Gloss
- JO-15M750:** 15±2 Gloss
- JO-50M750:** 50±2 Gloss

Recommended use:	• Parquet and flat parts		
Application method:	Spruzzo		
Product Preparation:	by weight:		by volume:
		JO-xxM750 100	same ratio as the procedure by weight
	hardener	FC---M070 30	
thinner	DF---M008 20 - 40		

Chemical-physical characteristics

Solid content (%)	25 ± 2
Specific gravity (g/cm ³)	0,94 ± 0,03
Viscosity DIN 4 (s) at 23°C	35 ± 5
Pot life (h)	6

Application characteristics

Recommended application weight	max 120 g/m ²
Number of coats	Max 2

General remarks on the application system

Drying at 20°C e 45-65 RU% : 100 g/m²

Dust free	20'
Touch free	40'
Stackable	8 h

Substrate preparation: Either JL---M070 or JL---M071 perfectly suit as sealer in anti-yellowing painting system. However, it may be applied on any type of PU, polyester or UV basecoats, or used as a basecoat itself when applied in two coats.

General remarks

The product has unlimited shelf life. However, after prolonged storage, some settlement may occur. It is therefore advisable to homogenize the product well before using it.